

TABLE II

Cup Head Thickness (*)

Observer	Min		Max		Avg. (**)	
	<u>1</u>	<u>2</u>	<u>1</u>	<u>2</u>	<u>1</u>	<u>2</u>
Remington	.0262	.0261	.0270	.0270	.02661	.02663
Federal	.0265	.0265	.0268	.0267	.02655	.02654
Winchester	.0270	.0270	.0275	.0275	.02728	.02728
CCI #200	.0262	.0262	.0266	.0266	.02640	.02640
CCI #250	.0260	.0260	.0267	.0267	.02641	.02641

*Loose primers with mixture removed

**The same 10 cups in each product were tested by each observer

83

CONFIDENTIAL