

TABLE 6

7mm EXPRESS REMINGTON

CASE WEB THICKNESS MEASUREMENTS

Code	No. Samples	Thickness (Inches)			Remarks
		Avg.	Max.	Min.	
*M09I	6	.048	.049	.047	Returned by distributors
N22B	3	.059	.060	.058	Control
M08I	1	.046	.046	.046	Enlarged primer pocket; fired by Paisley
M08I	1	.051	.051	.051	Fired by Paisley; appeared normal

- Loneke web thickness as per 280 Remington product drawing:

.055" to .070"

- * The individual readings for these samples were:

1. 0.048"
2. 0.043"
3. 0.047"
4. 0.049"
5. 0.048"
6. 0.048"