Changes from last report in bold.	wŵ.
ENCINEEDING	STAFF MEETING
ENGINEERING	<u>SIAFF MEETING</u>
Minutes from	n 1-3-06 Meeting
~~~~	********
MODEL 7	
<u>MODEL 700</u>	
J.Mead – Design and evaluate using a	plastic follower for both M700 and M7 rifles.
Design complete 9-15-05. (T.Powers)	Initial quotes received 10-4-05. Quotes received on
15-06. Testable parts by 2-17-06.	Redesigned 3-D Printer prototypes to review by 1-
G.Sietsema - Feasibility of using HIS j	process for nile barrels. Feasibility study complete by
1-30-06.	
	6 8mm SPC. Complete by 12-30-05. J.Kast –
	EM – F Ogrodnik is reviewing. 1 st prototypes made ated from vendor 1-4-06. Work Order by?
	r XR-100 is not user friendly. If 40-X version of new ring of 2006 then we may have to reengineer the
process to make it more ergonomic. O	n Hold. Production has 2,000 sears ready. Next
production of XR-100's is December 2	<del>00</del> 6.
J.Mead – change M700 youth pad to n J.Smith. TRT to make prototypes to ch	hatch M700 not shotgun youth. Coordinate with neck by 12-30-05.
J.Mead - Change printary cam angle o	n M700 bolt handles to reduce impact dings. Status o
PMI quotes?	
	ope holes. They need to be more rigid and have a
raised ring or thread to lock into thread	ed receiver holes better. Samples by 1-30-06.
MODEL 7600	
MODEL 750	
C:\Program Files\tcdl\CrackerLoaderREM\REME Page 1	mail\rawblob\20060206090340A00002700.doc

Subject to Protective Order - Williams v. Remington

# Changes from last report in bold.

#### **MODEL 7400**

**J.Mead** – Redesign bolts to prevent ejectors sticking back during proof. – J.Kast. One design to Production to tested 12-13-05. Test with moved ejector hole by 12-21-05. First function check done and ok. Second proof test done and ok. Need to test function with short and long action by? Second design (set serew to retain ejector) to tool room complete by?

### **MODELS 572 AND 552**

### **METAL FINISH & COLOR**

G.Sietsema – Test powder coating plastic trigger guards. D.Sampson has samples at PPG to test and evaluate by 10-30-05. Info received from PPG 10-24-05. PPG was on site to process parts 11-9-05. Must preheat parts to be consistent. Tested pre-heaters 12-22-05. Feasibility study by 1-10-05.

#### **MODEL 870**

- J.Mead Add detent to 20 gauge similar to 12 gauge for cost savings. Design complete 6-30-05. Cost analysis complete and favorable. Tooling, T&P, etc required. Production release by December 2005. Tooling details quoted. Need mag cap with detents – out for quotes. By?
- J.Mead Testing 12 gauge synthetic magazine cap. Prototypes in the Test Lab. Results by 10-15-05. Getting samples of new "super-tough" material, ST100 to test by 10-15-05. 26 (Delrin 570) samples made by CTM to test lab to test 1-4-06. (T.Powers) Test lab to finish testing by 1-30-06.

## **BARRELS**

### **ROUND RECEIVERS**

- S.Perniciaro Coordinate 1st article approval from Kerner. Samples failed for incorrect heat treat and out of position fire control mounting hole. New samples at Remington heat treat to check for hole movement by 10-12-05. Complete. E.Aiello getting Kerner to requite with Remington doing the heat treating. Status 30 heat treated samples by 1-7-06.
- G.Sietsema Poor broach finish on SST receivers. Change heat treat and make receivers harder. Tested 4-26-05. Results inconclusive. Running parts through all operations to verify the rest of machining. Plan by 5-31-05 for outside bar stock supplier. Test re-heat treated bars by 6-30-05. New Date 7/22/05. 3,826 # (64 bars) H.T.'d at Remington. Will run on engineering order 8-12-05. Need to confirm no issues with Operation 10 and improved broaching by 9-15-05. Complete and good. Need to order 40,000# to new specs. Steel mill to advise on availability by 10-14-05. Order is in and material due 2-10-06.

C:\Program Files.tcdl:CrackerLoaderREM\REMEmail\rawblob\20060206090340A00002700.doc

Page 2

Subject to Protective Order - Williams v. Remington

# Changes from last report in bold.

# **ROUND RECEIVERS (CONT)**

#### G.Sietsema – Review process to deburr receivers.

- EH Will try electro-chemical deburr (electro-polish) proposal received 9-15-05. Estimated 95 parts/hour and \$400,000 capital. Next step for project by 10-21-05. Need \$7,500 for more tooling to test. On hold.
- High Energy samples not feasible.
- Almco is looking at a heavy porous media to test by 11-29-05. 1st test failed. 2nd test 12-15-05 looks favorable. Will test with longer cycle time by 1-16-06 with larger tub.
- Developing brush deburr process reviewed 12-7-05. Samples sent to Weiler 12-15-05 to receive back 1-15-06. Weiler tech rep. at Remington by 1-15-06.

## **STOCKS**

- J.Mead -Coordinate upgrading all stock drawings and PPI with E-Town. Wood stocks by 10-31-05. Working on standardizing inletting by 1 30-06 – Tom Powers.
- S.Perniciaro –Need to establish plan to work with HS to get in good stocks in a timely manner. Project turned over to Ed Owens to complete. Bob Orf will review a new gage design with Joe Diliberto to send to HS. By 1+15-06

## **OTHER**

D.Shumway – Status of easy to use system to access Process records. Process reviewed with Production and approved. C.Vallabhaneni to set up priority list of operations and determine timing and resources.

G.Sietsema- Salts bleeding out of barrel sets. Tested in production with "No-Bleed". Problem with too much oil dripping from components

- Testing cleaner from WinTech. Initials results good.
  - Large test completed 9-30-05.
- Install No-Bleed and cleaner in color line by 12-10-05. ON HOLD
- J.Mead Design new grip cap with the ability to have different inserts used; e.g., Ducks Unlimited, RMEF, etc. By 12-20-05.

CUSTOM SHOP C.\Program Files\teditCrackerLoaderREM\REMEmail\rawblob\20060206090340A00002700.doc Page 3

Subject to Protective Order - Williams v. Remington