

REMINENT

REMINENT ARMS COMPANY

ENGINEERING DEPARTMENT

TEST REPORT SHEET

Powder Metal Sear

SUBJECT: TRIGGER PULL AS A FUNCTION OF

DRY CYCLING AND CONDITIONS

11-10-65

Trigger	555 PM	555 PM	555 PM	413 PM	413 PM	413 PM	413 PM
	NO SEAR LOAD	WITH SEAR TO CAM AS AT END OF CYCLING	SEAR TO CAM SURFACE WIPED NO. 000 SANDPAPER	NO SEAR LOAD	WITH SEAR TO CAM AS AT END OF CYCLING	SEAR TO CAM SURFACE WIPED NO. 000 SANDPAPER	SEAR TO CAM SURFACE WIPED NO. 000 SANDPAPER
DRY	165	165	165	165	165	165	165
CYCLES	4.00	4.75	5.00	4.00	6.50	6.50	6.50
Nov 5 AM		5.25	5.25		6.00	6.50	
		5.00	4.75		5.75	6.25	
		5.25	5.50		5.75	6.50	
		4.75	5.00		6.25	6.50	
		5.0	5.1		6.05	6.45	
1000	4.25	7.25	9.25	4.25	9.50	10.50	
Nov 5 PM		9.75	9.00		9.50	10.00	
		8.25	8.75		9.75	9.75	
		7.75	8.75		9.75	10.50	
		9.00	9.00		9.75	9.50	
Nov 6		8.4	8.95		9.65	10.05	
1000			7.50			6.75	
Nov 8 AM			6.50			7.00	
REMARKS			6.75			7.00	
			6.50			6.75	
			6.25			7.00	
			6.7			6.90	
2000	4.25	10.50	8.50		8.00	7.75	7.00
Nov 8 Noon		9.50	10.00		6.75	7.75	6.75
		10.75	9.50		6.50	8.00	6.50
		10.75	10.75		7.00	8.00	6.75
		11.25	10.00		7.25	8.00	6.25
Nov 9		10.55	9.75		7.10	7.90	6.60
2000			10.75				5.50
Nov 9 AM			9.25				5.00
			8.75				5.25
			9.25				5.00
			8.00				5.00
			9.10				5.10
3000	4.00	14.50	12.00	4.00	5.00		5.50
Nov 12 AM		9.25	13.00		5.75		5.25
		8.25	11.00		5.25		5.25
		9.25	13.00		5.25		5.25