

REMINGTON ARMS COMPANY, INC.

ENGINEERING DEPARTMENT COMPUTATION SHEET

SHEET NO 1

TITLE: POWDER METAL SPAR TEST
 SUBJECT: M700 MEASURING MACHINE TRIGGER PELLETS
 REF: OF 2000 3000 DRY CYCLES AAH

PROJ NO

WORKS

DATE: 8/23/65 19

CYCLE	154225	153959	139457	139312	139555	139413
NUMBERS	STD GUN	STD GUN	P.M.C.	P.M.C.	P.M.	P.M.
	457 F.C.	312 F.C.	413 F.C.	555 F.C.	959 F.C.	225 F.C.
2000-2050	—	5.2-5.4	—	5.2-5.7	6.4-7.0	5.0-6.0
2050-2100	—	5.3-5.5	—	5.4-5.9	6.3-7.2	5.8-6.0
2100-2150	—	5.3-5.5	6.0-7.3	5.6-5.9	5.8-7.1	5.9-6.1
2150-2200	5.6-6.5	5.4-5.6	7.2-7.5	—	6.2-6.9	6.0-6.2
2200-2250	5.6-6.5	5.5-5.9	6.0-7.4	—	6.1-6.4	6.0-6.2
2250-2300	5.8-6.5	5.8-6.7	6.8-7.4	6.4-7.0	6.4-7.5	6.1-6.3
2300-2350	5.8-6.4	5.9-6.1	7.0-7.5	6.7-7.2	5.6-6.4	6.1-6.3
2350-2400	6.0-6.2	6.0-6.3	7.2-7.6	7.3-7.5	5.2-6.8	6.2-6.4
2400-2450	6.1-6.4	6.1-6.4	7.2-7.6	—	5.2-6.2	6.2-6.4
2450-2500	6.0-6.5	6.2-6.5	7.4-8.1	6.7-7.1	—	6.3-6.4
2500-2550	5.9-6.7	6.1-6.4	7.8-8.2	—	—	6.2-6.4
2550-2600	5.9-6.7	6.3-6.7	7.7-8.3	—	—	6.3-6.5
2600-2650	5.9-6.5	6.2-6.5	7.9-9.3	7.8-8.1	—	6.3-6.5
2650-2700	5.8-6.7	6.3-6.8	7.8-8.8	7.8-8.0	6.8-8.5	6.2-6.5
2700-2750	5.8-6.8	6.4-6.8	7.9-8.7	7.6-8.0	—	6.2-6.5
2750-2800	5.9-6.8	6.1-6.7	7.3-9.2	7.6-8.1	6.1-7.3	6.3-6.5
2800-2850	6.1-6.9	6.2-6.5	7.9-7.9	7.8-8.3	6.7-7.9	6.4-6.6
2850-2900	5.9-6.8	—	8.0-9.4	7.7-8.0	6.7-7.2	6.3-6.5
2900-2950	6.3-6.9	6.8-7.1	8.1-9.2	7.7-8.3	7.0-8.1	6.4-6.6
2950-3000	6.4-6.8	6.9-7.2	8.3-9.4	7.7-8.2	7.3-8.3	6.3-6.6
	457	312	413	555	959	225