

5/10/71 *Spencer*

SNIPER STOCK FINISH

1. 1 STAIN COAT - NGR STAIN
2. 1 DIP COAT URETHANE SEALER
3. 2 DIP COATS VINYL TOP COAT (FLAT)

NOTE: SEALER & TOP COAT BAKED
BETWEEN COATS

1. MOISTURE PICK UP IN 72 HOUR WATER
IMMERSION - 5%
2. ADHESION - NO LIFT WITH FIRM "NICKEL TEST"

RECEIVED
OCT 29 1971
R. M. ADAMS, JR.