

EDL M700 LONG ACTION STOCK STRENGTH  
 RAM STATIC POUNDS LOAD FOR CRACKING AT "B"  
 MEAS/TEST LAB JULY 1978

|                         |     |                               |              |                               |                            |                             |                             |
|-------------------------|-----|-------------------------------|--------------|-------------------------------|----------------------------|-----------------------------|-----------------------------|
| RAM STATIC POUNDS LOAD. | 550 | D                             |              |                               |                            |                             | MAX 560                     |
|                         |     | D                             |              |                               |                            |                             |                             |
|                         | 500 |                               |              |                               |                            |                             |                             |
|                         |     | PD                            |              |                               | MAX 470                    |                             | MEAN 463                    |
|                         | 450 | F                             |              | MAX 440                       |                            |                             |                             |
|                         |     | OFF                           |              |                               |                            |                             |                             |
|                         | 400 | PPDDDN                        | MAX 400      |                               |                            | MAX 400                     | MIN 400                     |
|                         |     | DNF                           |              |                               | MEAN 377                   |                             |                             |
|                         | 350 | PPPDNN                        |              | MEAN 355                      |                            | MEAN 352                    |                             |
|                         |     | DN                            | MEAN 327     |                               | MIN 330                    |                             |                             |
|                         | 300 | DNF                           |              |                               |                            | MIN 300                     |                             |
|                         |     | FF                            |              | MIN 270                       |                            |                             |                             |
|                         | 250 |                               |              |                               |                            |                             |                             |
|                         | 200 | N                             | MIN 200      |                               |                            |                             |                             |
|                         |     | MAX LOAD AT "B" CRACK FAILURE | NO REINFORCE | FIBERGLASS REINFORCE AT "B+C" | BRASS PIN REINFORCE AT "B" | WOOD DOWEL REINFORCE AT "B" | WOOD DOWEL REINFORCE AT "B" |
|                         |     |                               | 8 STOCKS     | 7 STOCKS                      | 7 STOCKS                   | 4 STOCKS                    | 6 STOCKS                    |

8-10-78  
 A. A. W.