

D. L. Koshler	Service Engineering	
R. P. Skow	Plant Metallurgist	4-30-73

CORROSION TESTS (M. L. 2022)

Five pieces of 2014-T6 which had been sprayed with different corrosion protection solutions, baked at 450°F for one hour and then were subjected to a six day salt spray test, were evaluated to determine the amount and depth of corrosion. Presented below are the results.

<u>Sample</u>	<u>Solution</u>	<u>Treated Area</u>	<u>Untreated Area</u>
M. L. 2022	LPS #1	Uniform attack to .001".	Uniform attack to .001".
M. L. 2023	LPS #2	Intermittent attack with intergranular corrosion to .0015".	Uniform attack to .0015".
M. L. 2024	LPS #3	No attack.	Uniform attack to .0015".
M. L. 2025	Spray on 706	Uniform attack and intergranular corrosion to .0015".	Uniform attack and intergranular corrosion to .0015".
M. L. 2026	Spray on 711	Uniform attack and heavy intergranular corrosion to .0015".	Uniform attack and heavy intergranular corrosion to .0015".


R. P. Skow

RPS/mlj

4-30-73

Dick

Barrett

McIntire
Engineering
in formal of test