
From: Ronkainen, Jim
Sent: Tuesday, October 28, 2008 8:43 AM
To: Dwyer, John
Subject: FW: XMP Trigger Break Strength
Attachments: 700XMP External Adjust Trigger Strength10-28-08.xls

Sean,
FYI.

Jim Ronkainen
Staff Engineer
Remington Arms Co. Inc.
R&D Technical Center
315 W. Ring Road
Elizabethtown, KY 42701
(270) 769-7613 (phone)
(270) 737-9576 (fax)
jim.ronkainen@remington.com
visit us at www.remington.com

From: Sietsema, Glen D.
Sent: Tuesday, October 28, 2008 7:28 AM
To: Perniciaro, Stephen; Becker, Craig
Cc: Rabbia, James A.; Jiranek, Marlin R.; Wright, MaryAnn; Franz, Scott; Ronkainen, Jim
Subject: XMP Trigger Break Strength

Attached is the break strength of the triggers plated last week.

20 samples tested.
Load to failure (lbs)
Average: 68
Max: 84
Min: 56

Glen D. Sietsema
Metallurgical Engineer
Remington Arms Company, Inc.
14 Hoefler Ave.
Ilion, NY 13357
(315) 895-3234 Phone
(315) 895-3407 FAX
glen.sietsema@remington.com
visit us at www.Remington.com