Summary of firing results on 5mm Rem. Mag. at Ilion Research Division. All rounds were measured for pressure and case failures noted. Guns were measured for manufacturing adherence to model drawing dimensions and were in tolerance. The results shown reflect the expected performance of present warehouse stock.

Meas. Pressure Range 5mm	32,000 psi 42,000 (Normal) Proof	Úp to 55,000 psi	55,000 to 50,000 psi	60,000 65,000	65,000 Up
No. Rounds Fired		2250	121	157	105
No. Failures		0	- 19	33	33
% Failures		0	16	21	31

CHM:T 2-23-68