

EXHIBIT

SALT SPRAY TEST

USING PROTECTIVE COATING OVER UNPROTECTED STEEL

	1	2	3	4	5	6	7	24	48	72	Hours
Control	*										
Plant Oil	x	*									45¢/Gal. Before Diluted With Water
Hoppe's No. 9	x	*									
Dullite EZ Oil	x	x	*								
WD-40	x	x	x	x	x	x	x	x	x	x	\$1.57/15 Oz. Can
D-5010	x	x	x	x	x	x	x	x	x	x	\$4.67/Gal. in 55 Gal. Drum
CRC Mask	x	x	x	x	x	x	x	x	x	x	
Medtronic Oil	*										
Block	x	*									
Rlg	x	*									
TSI 300	x	x	*								
Anderol	x	x	x	x	*						

Legend: x - No Failures
* - Failure Point

3/18/70

EXHIBIT 1

WIL01965