

TABLE 7

7mm EXPRESS REMINGTON

CASE HARDNESS TEST

<u>Code</u>	<u>Hardness (DPH)</u>		<u>Remarks</u>
	<u>Rim Area</u>	<u>Web Area</u>	
M08I	189.5	215.5	Enlarged primer pocket; fired by Paisley
M08I	187.0	222.0	Appeared normal; fired by Paisley
N22B	185.5	222.8	Control

Note: The DPH figures shown are averages of two symmetrically placed readings. The locations do not coincide with those used by Lonoke. The minimum Lonoke hardness specification nearest to the rim area is 165 DPH. The minimum specification nearest the web area is 180 DPH.

ADMCD - 7/80

WIL06765