

EDL M700 LONG ACTION STOCK STRENGTH
 RAM STATIC POUNDS LOAD FOR CRACKING AT "B"
 MEAS/TEST LAB JULY 1978

RAM STATIC POUNDS LOAD	550	D					MAX 560
		D					
	500						
		PD			MAX 470		MEAN 463
	450	F		MAX 440			
		OFF					
	400	PPDDDN	MAX 400			MAX 400	MIN 400
		DNF			MEAN 377		
	350	PPPDNN		MEAN 355		MEAN 352	
		DN	MEAN 327		MIN 330		
	300	DNF				MIN 300	
		FF		MIN 270			
250							
200	N		MIN 200				
		MAX LOAD AT "B" CRACK FAILURE	NO REINFORCE	FIBERGLASS REINFORCE AT "B & C"	BRASS PIN REINFORCE AT "B"	WOOD DOWEL REINFORCE AT "B"	WOOD DOWEL REINFORCE AT "B"
			8 STOCKS	7 STOCKS	7 STOCKS	4 STOCKS	6 STOCKS

8-10-78
 A. A. W.