

REMINGTON ARMS COMPANY, INC.
Firearms Research Division

January 5, 1981

Xc: J.W.Brooks
D.E.Bullis

TO: J. R. SNEDEKER
FROM: C. J. MILLER - R. E. NIGHTINGALE
SUBJECT: MODEL ⁷~~700~~ CARBINE
Work Order: C 1856

INTRODUCTION

Four Model 700s with undersized and shortened barrels were supplied to the Measurements Lab for strength evaluation.

SYNOPSIS

The two Model 700s tested passed our most severe strength tests.

PROCEDURE

The two Model 700s with barrels undersized on the outside diameter by .120" and shortened by 4 inches were chosen for testing. The .100" O.D. undersized barrels were not tested.

The first rifle (#B6261719) had a strain gage applied to the barrel for pressure measurements. Five proof rounds were fired and the barrel's O.D. was measured at one inch intervals starting at the muzzle. Then a super proof load (52.4 gr. of IMR 4198 and a 220 gr. bullet) was fired.

The second 700 Carbine (#B6261940) was proof tested. Then four 220 grain bullets were forced into the barrel and a super proof load was fired.

RESULTS

There was no measurable or visual damage to either barrel. The stocks were broken due to gases escaping through or by the bolt.

The peak pressures measured by strain gage technique on B6261719 with super proof was 192,000 PSI-Strain.

The peak pressure on rifle #B6261940 with super proof and 4 bullets estimated (from other 700 testing) to be 400,000 PSI-Strain.

CJM:REN:T
Research Measurements Lab

		1	2	3	4	5	6	
		1 st Proof	2 nd Proof	3 rd Proof	4 th Proof	5 th Proof	Super Proof	
1								1
2	Muzzle	.537	.537	.537	.537	.537	.537	2
3	1"	.537	.537	.537	.537	.537	.537	3
4	2"	.537	.537	.537	.537	.537	.537	4
5	3"	.537	.537	.537	.537	.537	.537	5
6	4"	.537	.537	.537	.537	.537	.537	6
7	5"	.537	.537	.537	.537	.537	.537	7
8	6"	.540	.540	.540	.540	.540	.540	8
9	7"	.551	.551	.551	.551	.551	.552	9
10	8"	.568	.568	.568	.568	.568	.568	10
11	9"	.598	.597	.598	.598	.598	.598	11
12	10"	.625	.626	.625	.625	.626	.625	12
13	11"	.655	.655	.655	.655	.655	.655	13
14	12"	.685	.685	.685	.685	.685	.685	14
15	13"	.718	.718	.718	.718	.717	.718	15
16	14"	.776	.775	.777	.776	.777	.777	16
17	15"	.885	.885	.885	.885	.885	.886	17
18								18
19								19
20								20
21								21
22								22
23								23
24								24
25								25
26								26
27								27
28								28
29								29
30								30
31								31
32								32
33								33
34								34
35								35
36								36
37								37
38								38
39								39
40								40