

CODE IDENT
10001

WS 1413

NAVAL ORDNANCE SYSTEMS COMMAND

DEPARTMENT OF THE NAVY

PURCHASE DESCRIPTION

COMPOUND, CORROSION PREVENTIVE, ULTRA-THIN, TRANSPARENT

1. SCOPE

1.1 SCOPE - This purchase description covers an ultra-thin transparent water displacing, corrosion preventive compound which may be applied by aerosol, brush, dip or spray.

1.2 CLASSIFICATION - The corrosion preventive compounds shall be of the following types, as specified:

Type I - Aerosol Application

Type II - Brush, Dip or Spray Application

2. APPLICABLE DOCUMENTS.

2.1 The following documents, of the issue in effect on date of invitation for bids, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

1. QQ-M-44 Magnesium Alloy, Plate and Sheet (AZ31B)
2. PPP-C-96 Cans, Metal, 28 Gage and Lighter
3. QQ-A-250/4 Aluminum Alloy Plate and Sheet, 2024

FSC 8030

Naval Ships Engineering Station

-2-

August 11, 1972

<u>W/S 14138 Test</u>	<u>Requirement</u>	<u>#711 Results</u>
#8. Corrosion Test - MIL-C-23411A:	No Pitting or Etching - Limited Weight Loss:	
<u>Metals</u>		
Brass	1.0	0.039 loss
Solder	20.0	0.910 loss
Zinc	7.5	0.006 gain
Magnesium	0.5	0.433 loss
Aluminum	0.2	0.009 gain
Steel	0.2	0.027 gain
#9. Leakage	None	None
#10. Flash Point °F.	125° F. Min. TOC Type II (Bulk) Fed. Std. 791, 1103.6 140° F. Min. TOC Type I (Aerosol) ASTM D 1310 55 T	130° F. Min.
#11. Film Thickness	0.15 mils or less	0.15 mils max.
#12. Sprayability	Sprayable	Sprayable
#13. Staining	None	None
#14. Removability	Remove easily with P-D-680	Easily Removable

In addition, we wish to state the following characteristics and qualities of our Product #711 Penetrant-Lubricant, Corrosion Inhibitor, Demoisurant:

COLOR, ASTMD 1500	3-1/2 L
API Gravity @ 60°F.	41.7
Specific Gravity, 60, 60°F.	0.8170
Viscosity, cs @ 100°F.	2.21
% Non-Volatile (Fed. Std. 791, 3480)	24.6
% Volatile (Fed. Std. 791, 3480)	75.4
Initial Boiling Point, °F.	250°F.
Pour Pblnt, °F.	Below -85
Falex Step Test	More Than 750

(Continued...)