

CHEMICAL & METALLURGICAL LABORATORY REPORT

TEST PERFORMED BY: R. Lefebvre

DATE: 9-23-81

PART NAME/MODEL: Browning BBR, Trigger

PART NUMBER:

SAMPLE SIZE: 1

REQUESTED BY: T. Scott

DEPT: R&D

REASON FOR REQUEST: Evaluation of competitive products.

HARDNESS: Rc 46-49 15N-84-85
HEAT TREAT/COMMENTS:

SCALE:

CHEMICAL ANALYSIS/COMMENTS: 1055

high residual chrome

RC- 46-49

1055

15N-84-85

E313009178100ED EXPS 1

CV 2581 C .56 S .347 MN .71 MO .02 CR .15 NI .04

P .327 SI .22 V .040 CU .319 PB .0028 BK 2890

OUT OF RANGE FOR BK CV