

DIE CASTING ALLOY DATA

E. F. LA CROSSE SALES, INC.
P. O. Box 64 470 S. Pearl St.
CANANDAIGUA, NY 14424
(716) 394-8043

SPECIFICATION	Aluminum							Zinc		Zinc-Aluminum			Magnesium
Commercial	380-1% 306	380-3% 308	360 309	218 —	43 304	13 305	Hi-Flo —	3 J468b 903	5 J468b 925	ZA-8 —	ZA-12 —	ZA-27 —	AZ91B 501A
SAE	A380.1	380.1	A360.1	518.1	C443.1	A413.1	—	B88-83 Z33521	B88-83 Z33530	B88-84 Z23530	B88-84 Z33530	B88-84 Z33540	AZ91B
ASTM	QQ-A- 591D-10	QQ-A- 591D-11	QQ-A- 591D-12	QQ-A- 591D-7	QQ-A- 591D-3	QQ-A- 591D-2	—	QQ-Z-363B AG40A	QQ-Z-363B AC41A	—	—	—	QQ-M-388
Federal													
ELEMENT													
Copper	3.0-4.0	3.0-4.0	0.6	0.25	0.6	0.6	2.0-3.0	0.25	0.75-1.25	0.8-1.3	0.5-1.25	2.0-2.5	0.035
Iron	1.3	2.0	1.1-2.0	1.0-1.8	0.8-2.0	2.0	1.0	0.10	0.10	0.10	0.075	0.10	—
Silicon	7.5-9.5	7.5-9.5	9.0-10.0	0.35	4.5-6.0	9.5-13.0	9.0-10.5	—	—	—	—	—	0.5
Magnesium	0.10	0.10	0.4-0.6	7.5-8.5	0.05-0.10	0.10	0.03	0.02-0.05	0.03-0.08	0.015-0.030	0.015-0.030	0.010-0.020	Balance
Manganese	0.50	0.50	0.35	0.35	0.35-0.50	0.35-0.50	0.30	—	—	—	—	—	0.13
Zinc	1.0	3.0	0.35-0.5	0.15	0.50	0.50	3.0	Balance	Balance	Balance	Balance	Balance	0.35-1.0
Nickel	0.50	0.50	0.50	0.15	0.50	0.50	0.15	—	—	—	—	—	0.03
Tin	0.35	0.35	0.1-0.15	0.15	0.15	0.15	0.10	0.003	0.003	0.002	0.002	0.002	—
Aluminum	Balance	Balance	Balance	Balance	Balance	Balance	Balance	3.5-4.3	3.5-4.3	8.0-8.8	10.5-11.5	25.0-28.0	8.3-9.7
Lead (max)	—	—	—	—	—	—	0.15	0.005	0.005	0.004	0.004	0.004	—
Cadmium (max)	—	—	—	—	—	—	—	0.004	0.004	0.003	0.003	0.003	—
PROPERTIES													
Tensile Strength (ksi)	47	47	46	45	33	43	50	41	48	54	58	61	34
Yield Strength (ksi)	23	23	24	28	14	21	22	—	—	42	46	53	23
Elongation (% in 2")	3.5	3.5	3.5	5.0	8.0	3.5	5-6	10	7	6-10	4-7	1-3	3
Shear Strength (ksi)	28	28	28	29	19	25	27	31	38	40	42	47	20
Fatigue Strength (ksi)	20	20	20	20	17	19	21	6.9	8.2	15	12	21	14
Specific Gravity	2.75	2.71	2.63	2.57	2.65	2.65	2.67	6.6	6.7	6.3	6.03	5.0	1.8
Lbs. per Cubic Inch	0.098	0.098	0.095	0.093	0.096	0.096	0.099	0.240	0.240	0.227	0.218	0.181	0.066
CHARACTERISTICS													
Machinability	Good	Good	Good	Very Good	Fair	Fair	Good	Excellent	Excellent	Excellent	Good	Good	Excellent
Castability	Excellent	Excellent	Good	Poor	Fair	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Good
Corrosion Resistance	Fair	Fair	Good	Excellent	Good	Good	Good	Good	Good	Good	Good	Good	Fair
Anti-Soldering	Good	Excellent	Good	Poor	Poor	Excellent	Good	Good	Good	Good	Good	Good	Good
Polishing	Fair	Fair	Fair	Excellent	Poor	Poor	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Anodizing Appearance	Fair	Fair	Fair	Excellent	Good	Poor	Fair	Good	Good	Excellent	Excellent	Fair	Good
Pressure Tightness	Good	Good	Excellent	Poor	Good	Excellent	Good	Good	Good	Good	Excellent	Fair	Good
Bearing Wear	—	—	—	—	—	—	—	—	—	Good	Excellent	Excellent	Fair

BARBER - PRESALE R 0117054

CONFIDENTIAL-SUBJECT TO PROTECTIVE ORDER
KINZER V. REMINGTON

BARBER - PRESALE R 0117054
R2518042